

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

N-Thermon[®] Primer

Description of the product Powerful adhesion, quartz sand primer, for **Deplast[®]** mortar.

Applications Used at smooth surfaces, like gypsum boards, polystyrene sheets and concrete, for enhancing the adhesion of **Deplast[®]** mortar or other cement slurry that will be applied. It can be applied over painted surfaces (with plastic or acrylic paint), prior to smooth-finished mortar.

Properties

- Remarkable adhesion on porous as well as smooth substrates
- It can accept cementitious slurries even after several days have passed from its application.
- Resistant to alkalies contained in the cement.
- Suitable for interior and exterior use.

Technical characteristics

Appearance	viscous liquid
Color	Light Red
Density (ISO 8962, DIN 51757)	1,32 g/cm ³
pH (ISO 1148, DIN 53785)	8-9
Consumption	330-400gr/m ²
Touch dry (25°C)	3 hours
Time to cover with cement mortars (25°C)	after 24 hours

Instruction for use **N-Thermon[®] Primer** is applied with brush, roller. After thorough cleaning and removal of loose particles and dust, apply 1 layer of the product. The application of cement mortar **Deplast[®]** can take place after 24 hours, without further limitations on the time it will take place.

Precautions

- **N-Thermon[®] Primer** must **NOT** be applied below +10°C
- Applied undiluted, or with a slight dilution (maximum 3%) with water.

Packing 5 kg, 15 kg in plastic containers

Cleaning of Tools Clean tools and other devices with plenty of water, immediately after use.

Storage Stability 12 months when kept sealed in its original container in dry and covered place.