

ESTABLISHED IN 1959

CONSTRUCTION CHEMICALS



www.neotex.gr • e-mail: neotex@neotex.gr

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.: +30 210 5557579, FAX: +30 210 5558482 THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.: +30 2310 467275, FAX: 2310 463442

Jointex[®]

Acrylic mastic for sealing joints

(E)	Properties
E	Technical (
	Appearance
	Density
	Hardness (S
	Elongation (
	Shrinkage
(e)	Consumptio
	Instruction

• ,	Jointex [®]	maintains	its	elasticity	in	а	wide	range	of	temperatur	es
-----	----------------------	-----------	-----	------------	----	---	------	-------	----	------------	----

- It shows excellent adhesion to many substrates and can be recoated with any water-based coating
- It is resistant to weathering, to ultraviolet radiation and to dilute acids, alkalis and detergents
- It does not contain organic solvents and it is environmentally friendly

Technical Characteristics

Appearance Homogeneous paste

1.5a/cm³ Density

Hardness (Shore A) 20±3

Elongation (+25°C) 250%

Shrinkage 3,5%

Jointex® seals about 6,5 linear meter joint with 1 cm²cross-section Consumption

Instructions for use

The sides of the joint where the product is to be applied should be free from dust, oil, grease or any poorly adhering material. It is suggested to use a solvent to clean the sides of the joint from dirt. It is not necessary to prime the surface (in case of very absorptive substrates, dilute Jointex® with water up to a ratio of 1:2 in order to prime the surface). The material is applied with a spatula.

Notes

After the application **Jointex**® exhibits low shrinkage. Drying time depends on thickness and weather conditions. The product should not be applied under humid conditions (e.g. rain), or if humid conditions are expected to prevail during the curing period of the film. In case of deep joints, the use of backing rod is recommended, so that the mastic adheres only to the sides of the joint. In case of sealing horizontal joints, where there is a possibility of accumulation of stagnant water, it is suggested that after the application of **Jointex**[®] the joint should be coated with **Neoroof**[®], **Neoproof**[®] **PU W** or **Silatex**[®] **Super** with a brush or a roller, along the joint and to a width greater than the width of the joint, in order to enhance impermeability to water.

Cleaning of tools Use plenty of water immediately after application.

Use water when the stain is still fresh and damp. In case of hardened Stain removal stains, use mechanical means or a paint remover.

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA .It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.



ESTABLISHED IN 1959

CONSTRUCTION CHEMICALS



www.neotex.gr • e-mail: neotex@neotex.gr

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.: +30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.: +30 2310 467275, FAX: 2310 463442

<u>Jointex</u>®

Colours	White and terracotta.			
Packing	1 kg, 5 kg & 15 kg plastic containers			
Storage stability	The product is stable for 2 years when kept unopened in its original container, protected from frost and direct sunlight.			



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA .It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.