

## Epoxol® Liquid

**Two-component bonding-sealing epoxy system,  
in fluid form**

### Description

Two-component solvent-free epoxy system, in fluid form, for repairing and bonding applications on horizontal surfaces and for sealing small gaps and openings

### Fields of application

- Leveling – repairing of floors prior to the application of resinous systems or coatings **Epoxol**®, **Neopox**®, **Neodur**®
- Anchoring applications, powerful bonding of metals, concrete, wood, ceramics, etc.



### Packing

Sets (A+B) of 6kg and 1kg

### Properties - Advantages

- Consists of pure resins and selected hardeners, free of solvents, extenders or fillers, offering very high mechanical and chemical resistance
- Excellent resistance to fresh and sea water, dilute acids, alkalis, petroleum products
- Easy and quick repair and leveling of horizontal surfaces
- Very high bonding ability
- Excellent adhesion on concrete, cement screeds, metal, stone, wood, etc.
- Ideal for difficult-to-reach areas on floors
- Can be also used in other mixing ratios apart from the standard ratio 1:1, depending on the application and the elasticity requirements

### Technical characteristics

Mixing ratio A:B (by weight)	a) 1:1 – Standard version, for bonding and repairing applications b) 2:1 – Hard version c) 1:2-2,5 – Elastic version
Density (EN ISO 2811-1)	1,03kg/L (±0,05)
Solids content by weight	100%

Solids content by volume	100%
Adhesion strength (EN 13892-8)	≥2,5N/mm <sup>2</sup>
Resistance to temperatures (dry loading)	-30°C min. / +80°C max.
<b>Consumption: ~1,05kg/m<sup>2</sup> per mm of thickness</b>	

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<70%
Application temperature (ambient - substrate)	+8°C min. / +35°C max.

### Curing details

Pot life (+20°C, RH 50%)	1,5-2 hours
Drying time (+20°C, RH 50%)	6-8 hours
Full hardening	~5-7 days

*\* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them*

### Appropriate primers on concrete substrate

	Primer	Description - Details
Solvent-free	<b>Epoxol® Primer SF</b>	Two-component, solvent-free epoxy primer for flooring applications
	<b>Epoxol® Primer SF-P</b>	Two-component, solvent-free epoxy primer, ideal in cases of substrates with increased porosity
	<b>Neopox® Primer WS</b>	Two-component, solvent-free epoxy primer for wet surfaces (without ponding water or rising moisture)
	<b>Neopox® Primer AY</b>	Two-component, solvent-free anti-osmotic epoxy primer, for floors with rising moisture
Water-based	<b>Acqua Primer</b>	Two-component water-based epoxy primer
Solvent-based	<b>Epoxol® Primer</b>	Two-component solvent-based epoxy primer

### Instructions for use

#### **Substrate preparation**

The substrate must be stable, clean, dry & protected from rising moisture, as well as free of dust, oil, grease, dirt and any loose or poorly adhering material. Depending on the substrate, proper mechanical preparation may be required to smooth out the irregularities, create an open-textured surface, and ensure optimum adhesion. In the case of non-porous and glossy surfaces, sanding improves the final result. If needed, cleaning of the surfaces, that are to be bonded, may be done with solvent **Neotex® 1021**.

**Priming**

For the stabilization of the substrate and sealing of pores, as well as for creating the optimum conditions for stronger adhesion of **Epoxol® Liquid**, it is recommended to apply the solvent-free epoxy **Epoxol® Primer SF-P** or an alternative appropriate **NEOTEX®** primer (see table), depending on the substrate. In cases of substrates with increased porosity, an additional priming layer may be required.

**Application**

The required quantity is removed from the containers with a different tool for each component separately. The two components are then mixed very well in the desired ratio with a suitable hand tool, until the mixture becomes homogeneous. The mixture is then spread on the application surface with a trowel or construction spatula, pressing it onto the surface in order to fill the gaps.

The standard mixing ratio for repairs and bonding is 1A : 1B w/w. Small deviations from this ratio do not have a significant effect on the final properties.

The mixing ratio of 2A : 1B w/w (hard version) renders a hard finish and is suitable for anchoring of reinforcements, floor repairs, etc.

The mixing ratio 1A : 2-2,5B w/w (elastic version) renders an elastic epoxy system, suitable for sealing small joints and gaps that are subject to contractions and expansions. This version must not be overcoated by other hard resinous systems or coatings.

**Special notes**

- **Epoxol® Liquid** should not be applied under wet conditions, or if wet conditions are expected to prevail during the application or the curing period of the product.
- Due to the nature of the material, its direct and continuous exposure to UV radiation may cause chalking over time
- In case of storage at low temperatures, the product acquires a very high viscosity and it is recommended to warm it up before the use, so that it returns to its normal rheological state.

<b>Appearance (mixture)</b>	Semi-transparent, yellowish
<b>Packing</b>	Sets (A+B) of 6kg and 1kg in plastic pails
<b>Cleaning of tools – Stains removal</b>	By <b>Neotex® 1021</b> immediately after application. In case of hardened stains, by mechanical means
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AgSB: 350g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <350g/l
<b>UFI code</b>	<i>Component A:</i> 2330-G03P-W00Y-NCRE <i>Component B:</i> 5030-Y0E9-M00G-Y15C



<b>Versions</b>	<b>Epoxol® Putty</b> , thixotropic epoxy system, for repairing and bonding applications, with high viscosity, in order to seal big gaps, without flowing
<b>Storage stability</b>	2 years, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight. It is advisable to avoid storage at temperatures below +8°C.

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275

[www.neotex.gr](http://www.neotex.gr) ● [export@neotex.gr](mailto:export@neotex.gr)