

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482 **THESSALONIKI:** Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neodur[®] FT Clear

Transparent, 2-component, aliphatic polyurea varnish ideal for the waterproofing of tiled surfaces

| Description of the product | Neodur[®] FT Clear is a technologically advanced, transparent, fast curing, brushable elastic polyaspartic varnish. It is ideal for waterproofing roofs and balconies that have been fitted with tiles. It offers high mechanical strength and long-term resistance to UV radiation without yellowing. | |
|---|--|--|
| Properties | High resistance to abrasion and mechanical stress | |
| | Zero water absorption | |
| | Highly resistant to UV radiation. It does not yellow even after many years | |
| | Crack bridging properties | |
| | Fast drying | |
| | Certified with CE (EN 1504-2) | |
| Technical characteristics | | |
| Appearance | Transparent | |
| Density (25°C) | 1,04±0,01g/cm ³ | |
| Mixing Ratio (weight prop.) | 1:1 | |
| Consumption | 700gr/m ² (for 2 layers) | |
| Pot life (+25°C) | 30 min | |
| Drying time (+25°C) | 5 hours | |
| Total hardening (+25°C) | 7 days | |
| Service Temperature | -35°C min / +60°C max | |
| Elongation (ASTM D412, +25°C) | 200% | |
| Surface humidity content | <4% | |
| Hardness Shore D (EN ISO 868:2003/ASTM 2240) | 25 | |
| Tensile Strength (ASTM D412, +25°C) | 22MPa | |
| Abrasion resistance | 80mg (Taber test CS 10/1000/1000, ASTM D4060) | |





ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482 **THESSALONIKI:** Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neodur[®] FT Clear

| X | Instructions for use | Surface preparation: The surface under the tiles should be dry. In case of moisture beneath the tiles, ventilators should be fitted before the application. The surfaces must be rough (not smooth) and thoroughly dry, free from dust, dirt, greasy and oily substances. In case of glossy tiles, it is necessary to grind the tiles and remove the glazy film. For mat tiles, the surface must be treated with Neosil® Bond in order to improve the adhesion of the following material. For applications where the tile grout is fresh (less than 1 year), it is necessary to apply Neodur® Polyurea M as a primer, diluted with Neotex® PU 0413 (50- 60%) with a consumption of 50 gr/m ² . If the tiles are not newly installed, then after treatment with Neosil® Bond , Neodur® FT Clear can be applied directly in two layers. |
|------|----------------------|---|
| | | Application: After very good stirring of the components A & B in the appropriate ratio, the mixture is applied onto the surface and spread thoroughly by brush or roller. |
| | Special notes | Neodur[®] FT Clear should not be applied when the temperature is below + 5°C. |
| Π | | In places where there are moving joints and at the entrance, ready expansion joint cover profiles should be used. Also pay attention to the details and mountings where there are gutters and metal grates. |
| | | • The surface should be dry during application and protected from rising moisture. |
| | | • Neodur[®] FT Clear is not suitable for the production of stone carpets. |
| A | Cleaning of tools | Immediately after application with solvent Neotex® 1021 . |
| (41) | Packing | Set (A+B) 8kg, 2kg |
| | Storage | 1 year if kept unopened in its original package, protected from frost and sunlight. |

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX[®] SA. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX[®] SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.





ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482 **THESSALONIKI:** Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neodur[®] FT Clear





1922

ΝΕΟΤΕΧ Α.Ε.Β.Ε Β. Μοίρα, Θέση Ξηροπήγαδο, Τ.Θ. 2315 19600, ΒΙ.ΠΑ Μάνδρα Αττικής

NEOTEX S.A V. Moira str., P.O. Box 2315 GR 19600 Industrial Area Mandra, Athens, Greece

19

1922-CPR-0386

Dop No/4950-46

EN 1504-2

Neodur[®] FT Clear

Σύστημα προστασίας επιφανειών σκυροδέματος

Surface Protection System for Concrete

Επικάλυψη

Coating

| Διαπερατότητα υδρατμών /Water Vapour Permeability | Κατηγορία/Class Ι |
|---|---|
| Αντοχή αποκόλλησης /Adhesion Strength | ≥1.5N/mm ² |
| Τριχοειδής απορρόφηση και | |
| υδατοπερατότητα/ Capillary Absorption | W<0.1Kg/m ² h ^{0.5} |
| Διαπερατότητα σε CO ₂ /Permeability to CO ₂ | S _D >50m |
| Αντίδραση στη φωτιά/Reaction to Fire | Ευρωκατηγορία F/Euroclass F |
| Επικίνδυνες ουσίες/Dangerous Substances | Σύμφωνα με 5.3/Comply with 5.3 |