

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482  
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

## Neotextile® NP

### Non-woven polyester reinforcement specially designed for waterproofing systems

#### Fields of application

- Suitable for reinforcement of coatings such as **Neoproof® Polyurea**
- Specially recommended for covering cracks and upstands
- Compatible with any building surface, including metallic, for affixing.

#### Properties-Advantages

- Applied easily
- It does not torn
- It does not require great consumption of coatings for its impregnation
- It increases durability and efficiency of waterproofing systems

#### Technical characteristics

Consumption of reinforced coatings: 3 kg/m<sup>2</sup>

Properties	Test Method	Mean Values
Weight	EN ISO 9864	100gr/m <sup>2</sup>
Static strength of resistance CBR	EN ISO 12236	480 N
Tensile strength	EN ISO 10319	2,8 KN/m
Cone drop test	EN ISO 13433	48 mm
Elongation at max. load	EN ISO 10319	≥ 50%
Thickness	EN ISO 9863/1	0,6mm

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482  
THESSALONIKI: Ionias Str., GR 57009 Kalochoi, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

## Neotextile<sup>®</sup> NP

---

**Instruction for use**

After the first layer of the coating is applied (the use of a primer is advisable for improving adhesion) place **Neotextile<sup>®</sup> NP**. At least two more coats are required for the complete coverage of the product.

---

**Storage stability**

Unlimited

---

**Packing**

- Roll 100 x 0,98 m
- Tape 10 m x 14 cm