

## **Neodur® Varnish W Mat**

**Transparent two-component water-based polyurethane  
varnish, with mat appearance**



### Description

Transparent two-component water-based polyurethane mat varnish, cured with aliphatic polyisocyanates, suitable for the protection and decoration of micro-cement coatings and various other construction surfaces.

### Fields of application

- Protection of decorative micro-cement coatings
- Protection and decoration of cementitious and metallic surfaces, natural stone, polyester, epoxy and other resinous systems in interior or exterior areas
- Ideal for application on walls – suitable also for floors of low traffic

### Properties - Advantages

- Offers a mat finish of high hardness, with anti-slip properties
- Protects against water absorption and enhances the mechanical strength of micro-cement coatings and several other substrates
- Offers long-term resistance to solar radiation and yellowing
- Excellent adhesion on numerous substrates
- Ideal for interior areas where solvent fumes are unwanted
- Eco-friendly & user-friendly
- High aesthetic result



### Packing

Sets (A+B) of 9kg, 3kg and 0,8kg

### Appearance (cured)

Transparent, mat

### Certificates – Test reports

- CE Certification acc. to EN 1504-2  
*Certificate of Conformity No. 1922-CPR-0386*
- Test report by the external independent quality control laboratory Geoterra (No. (No. 2023/333\_34)
- Complies with the V.O.C. content requirements acc. to the E.U. Directive 2004/42/CE

### Technical characteristics

Mixing ratio A:B (by weight)	90:10
Density (EN ISO 2811-1)	1,05kg/L (±0,05)
Gloss (60°)	20
Abrasion resistance (Taber Test, CS 10/1000/1000, ASTM D4060)	30mg
Adhesion strength (EN 1542)	≥2,5N/mm <sup>2</sup>
Flexibility (ASTM D522, 180° bend, 1/8" mandrel)	Pass
Scratch hardness (Sclerometer Test - Elcometer 3092)	5N
Skid resistance (EN 13036-4, wet surface, with 2,5% w/w addition of Neotex® Antiskid M)	>70 (PTV – slider 55)
Liquid water permeability (EN 1062-3)	0,01kg/m <sup>2</sup> h <sup>0,5</sup>
Permeability to CO <sub>2</sub> – Diffusion-equivalent air-layer thickness Sd (EN 1062-6)	>50m
Water vapour permeability – Diffusion-equivalent air-layer thickness Sd (EN ISO 7783)	>5m (Class II)
Resistance to temperatures (dry loading)	min. -30°C / max. +80°C
<b>Consumption: ~125gr/m<sup>2</sup> per layer (on properly prepared surfaces)</b>	

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<65%
Application temperature (ambient - substrate)	+12°C min. / +35°C max.

### Curing details

Pot life (RH 50%)	+12°C	1,5 hours
	+25°C	1 hour
Dry to recoat (RH 50%)	+12°C	28 hours
	+25°C	24 hours
Full hardening		~ 7 days
<i>* Low temperatures during application and/or curing prolong the above times, while high temperatures reduce them</i>		

### Instructions for use

#### Substrate preparation

The surface must be stable, clean, dry, protected from rising moisture and free of dust, oil, grease and loose materials. Any poorly adhering materials and older coatings should be removed, and the surface should be thoroughly cleaned by

proper mechanical or chemical means. Depending on the substrate, appropriate mechanical preparation may be required, in order to smooth out the irregularities, open the pores and create the optimum conditions for adhesion.

#### **Priming**

Especially in the case of micro-cement substrate, it is advisable to prime the surface with the hybrid primer **Neodur® Varnish PR** diluted 25-30% w/w with clean water.

#### **Application**

The two components A & B are mixed in the predetermined ratio (90A:10B w/w) and, after the addition of clean water in the appropriate ratio, they are stirred for app. 3 with a low-speed electric stirrer, until the mixture becomes homogeneous. The mixture is then left for app. 5 minutes inside the can and then, **Neodur® Varnish W Mat** is applied, diluted 20-30% w/w with water, in at least two layers by roller or brush. For enhanced anti-slip properties, it is recommended that the final layer of **Neodur® Varnish W Mat** is applied after the product has been mixed 1,5-2,5% w/w with the anti-slip additive **Neotex® Antiskid M**.

---

### Special notes

- **Neodur® Varnish W Mat** should not be applied under wet conditions, or if wet conditions or rainy weather are expected to prevail during the application or the curing period of the product
- It should not be applied on surfaces where water repellent impregnation materials (e.g., siloxane-based) or waxes have been applied in the past
- Depending on the porosity of the substrate, the application of multiple protective layers may be required to achieve full sealing. This is particularly important on cementitious substrates where no priming with **Neodur® Varnish PR** has been carried out, in which case the application of at least three layers of the varnish is deemed necessary.
- Depending on the intended use, the application of extra protective layers may be needed in order to form a protective film of increased total thickness.
- It is not recommended to apply **Neodur® Varnish W Mat** as a final layer on floors of parking garages or high traffic of vehicles


---

### Maintenance instructions

- In case of minor spills and stains, it is recommended to remove them as soon as possible by using a soft cloth along with warm clean water (temperature <+50°C)
- For the maintenance cleaning of the surface from dust and dirt, it is recommended to use a vacuum cleaner or a soft bristle broom. The use of hard brushes or wires to remove the stains should be avoided.
- For cleaning the surface from hardened stains, it is recommended to use a hard foam mop with a solution of water and ammonia (~3% dilution). Then, rinse off with clean warm water (temperature <+50°C) and dry the surface with a soft towel.

- In case of using commercial cleaning products, the use of neutral ones is recommended (pH between 7 and 10). Soaps or all-purpose cleaners containing water-soluble salts or harmful ingredients with high concentration in alkalis or acids should be avoided. Follow the manufacturer's recommendations with respect to the optimum dilution with water. In any case, the first time a commercial cleaning product is used, it is recommended that a trial is made in a small surface area.

<b>Appearance (cured)</b>	Transparent, mat
<b>Packing</b>	Sets (A+B) of 9kg, 3kg and 0,8kg in metallic containers
<b>Cleaning of tools – Stains removal</b>	By water immediately after application. In case of hardened stains, by mechanical means
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AjWB “Two-pack reactive performance coating”: 140g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <140g/l
<b>UFI code</b>	<i>A component:</i> UU50-P06D-Q00T-T9DG <i>B component:</i> CX50-50VT-1009-GMYJ
<b>Versions</b>	<b>Neodur® Varnish Gloss</b> , glossy solvent-based varnish <b>Neodur® Varnish Satine</b> , satin solvent-based varnish <b>Neodur® Varnish Mat</b> , mat solvent-based varnish <b>Neodur® Varnish W Gloss</b> , glossy water-based varnish <b>Neodur® Varnish W Satine</b> , satin water-based varnish
<b>Storage stability</b>	<i>A component:</i> 2 years, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight <i>B component:</i> 6 months, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight. Component B must be stored in an absolutely dry place, protected from frost and humidity. In case of contact with ambient moisture it can be polymerized inside the container.

 1922	
<b>NEOTEX S.A.</b> V.Moira str., P.O. Box 2315 GR 19600 Industrial Area Mandra, Athens, Greece 23	
1922-CPR-0386 DoP No.: 4950-94 <b>EN 1504-2</b> <b>Neodur® Varnish W Mat</b> Surface protection products Coating	
Water vapour permeability	Class II
Adhesion strength	≥1,5N/mm <sup>2</sup>
Capillary absorption and permeability to water	W<0,1Kg/m <sup>2</sup> h <sup>0.5</sup>
Permeability to CO <sub>2</sub>	S <sub>D</sub> >50m
Reaction to fire	Euroclass F
Dangerous substances	Complies with 5.3

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275