

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

GILUFORM – SP 12

Description of the product

Giluform SP 12 is a powder, mixable in a very manner, forming an easy flowing mass for the manufacture of reliefs, models and castings. **Giluform SP 12** is not suitable for supporting structures.

Properties/Advantages

- Simple processing
- Quick solidification without additives
- Porcelain-like structure of the cast material
- No drying, no firing
- Accurate reproduction, also of finest details
- Surface-treatment possible with all commercial colours
- Not Harmful to skin or injurious to health

Technical Characteristics

| | |
|----------------------|--|
| Appearance | Fine powder |
| Mixing ratio | 4kg powder- 1Lt water (mixed volume 2,4lt) |
| Working time | 17 min |
| Solidification point | 25 min |
| Surface hardness | Above 300MPa |

Instructions for use

To casting form, for example a flexible plastic mould, is to be set up in a level position. Next strew the plaster in the above mentioned ratio into the water, allow to soak, stir for approx.. 1min., taking care not to cause air bubbles. In order to mix larger quantities it is advisable to use a mixing machine. Pour the easy flowing mix in a thin stream into the middle of the form until the surface of the form is covered with a bubble free layer. The rest of the mix can be poured more rapidly. Approximately 45min. after casting the relief or model can be removed from the mould. Place the casting, which is becoming warm onto wooden lathes until it is completely set, which takes about 8 hours, the surface may be treated in any desired manner, e.g. with dispersion or opaque colours.



ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

GILUFORM – SP 12

Special Notes

- It is important to use only pure water and clean receptables.
- Do not exceed the working time.

| | |
|--------------------------|--|
| Colours | White or brick-red |
| Packaging | Paper bag with foil liner 25kg |
| Storage stability | At least 12 months in closed, vapour-proof packages. |



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX[®] SA. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX[®] SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.