



**ATHENS:** V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482 **THESSALONIKI:** Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

## Neotex<sup>®</sup> Inox Primer

## Water-based primer for inox, aluminium, galvanized surfaces

Description – Fields of application	<b>Neotex</b> <sup>®</sup> <b>Inox Primer</b> is a one-component, water- based primer, with very strong adhesion on glossy non-porous substrates such as inox, aluminium, galvanized surfaces, tinplate, glass
Properties	<ul> <li>One-component product, easy to apply</li> <li>Exhibits high adhesion strength on most glossy non-porous substrates</li> <li>Does not require any treatment prior to painting over it, offering excellent adhesion strength to water-based, solvent-based or solvent-free coatings that may be applied on top.</li> <li>Environmentally friendly &amp; user friendly</li> <li>Does not include any toxic ingredients or solvents</li> </ul>
Technical characteristics	
Density (EN ISO 2811.01)	1,04±0,01g/ml
Viscosity (ASTM D562, +25°C)	60±2KU
Drying time (+25°C)	1 hour
Dry to recoat (+25°C)	10 hours
Consumption	60-75ml/m² in one layer

V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AiWB "One-pack performance coatings": 140g/l (Limit 2010). V.O.C. content of the ready to use product <10g/l





**ATHENS:** V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482 **THESSALONIKI:** Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

## Neotex<sup>®</sup> Inox Primer

Instructions for use	<i>Surface Preparation</i> : The surface should be dry, free from dust, dirt, greasy and oily substances, as well as from any poorly adhering coatings. In case it is not possible to thoroughly clean the surface from existing poorly adhering coatings, it is advisable to grind with fine sandpaper and then clean the surface with solvent <b>Neotex</b> <sup>®</sup> 1021.	
	Application: <b>Neotex<sup>®</sup> Inox Primer</b> is then applied in a single thin layer by enamel paint roller.	
Special notes	• Application conditions: Substrate moisture < 4% / Relative air humidity < 65% / Minimum ambient temperature: +10°C	
	Low temperatures and high humidity prolong drying times	
	The material should not be applied under conditions of high humidity	
	• The material must be applied in a single thin layer	
Cleaning of tools	Use water immediately after application.	
Packing	3L and 1L in plastic pails	
Storage stability	2 years in its unopened, original container in absolutely dry place protected from direct sunlight and low temperatures.	

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.